

| Select Casement | NAFS Ratings | NFRC/Energy Star: NFRC | AAMA/WDMA/CSA/1.S.2-/A440-08: LC-PG60-C | | | Size Tested: (34"x80") | |
|------------------------------------|---------------|------------------------|---|-----------------------------|-----------------------|-------------------------|---------------------------------|
| Glass Options | Energy Rating | U-value (metric) | U-value (imperial) | Solar Heat Gain Coefficient | Visible Transmittance | Condensation Resistance | Canadian Energy Star Zones 2015 |
| Clear | 17 | 2.4 | 0.42 | 0.51 | 0.53 | 45 | No/non |
| Clear w Grilles | 14 | 2.4 | 0.42 | 0.46 | 0.48 | 45 | No/non |
| LoE/Argon | 30 | 1.6 | 0.29 | 0.46 | 0.52 | 59 | 1 2 |
| LoE/Argon w Grilles | 27 | 1.6 | 0.29 | 0.41 | 0.47 | 59 | 1 |
| Energlass | 31 | 1.6 | 0.28 | 0.46 | 0.52 | 61 | 1 2 |
| Energlass w Grilles | 28 | 1.6 | 0.28 | 0.41 | 0.47 | 61 | 1 |
| LoE/Argon-LSG | 19 | 1.6 | 0.28 | 0.25 | 0.45 | 61 | 1 |
| LoE/Argon-LSG w Grilles | 18 | 1.6 | 0.28 | 0.23 | 0.41 | 61 | 1 |
| Energlass-LSG | 21 | 1.5 | 0.27 | 0.25 | 0.45 | 63 | 1 |
| Energlass-LSG w Grilles | 19 | 1.5 | 0.27 | 0.23 | 0.41 | 63 | 1 |
| Triple Clear | 30 | 1.6 | 0.29 | 0.46 | 0.49 | 61 | 1 2 |
| Triple w Grilles | 28 | 1.6 | 0.29 | 0.42 | 0.44 | 61 | 1 |
| Triple LoE/Argon x 1 LSG | 26 | 1.2 | 0.22 | 0.23 | 0.41 | 71 | 1 2 |
| Triple LoE/Argon x 1 LSG w Grilles | 24 | 1.2 | 0.22 | 0.21 | 0.37 | 71 | 1 2 |
| Energls Plus Argon LSG | 29 | 1.0 | 0.18 | 0.20 | 0.35 | 79 | 1 2 3 |
| Energls Plus Argon LSG w Grilles | 28 | 1.0 | 0.18 | 0.18 | 0.32 | 79 | 1 2 3 |
| Triple LoE/Argon x 1 | 36 | 1.2 | 0.22 | 0.41 | 0.48 | 71 | 1 2 3 |
| Triple LoE/Argon x 1 w Grilles | 34 | 1.2 | 0.22 | 0.37 | 0.43 | 71 | 1 2 3 |
| Energls Plus Argon | 38 | 1.1 | 0.19 | 0.39 | 0.47 | 78 | 1 2 3 |
| Energls Plus Argon w Grilles | 37 | 1.1 | 0.19 | 0.36 | 0.43 | 78 | 1 2 3 |

| Select Awning | NAFS Ratings | NFRC/Energy Star: NFRC | AAMA/WDMA/CSA/1.S.2-/A440-08: CW-PG70-AP | | | Size Tested: (40"x63") | |
|------------------------------------|---------------|------------------------|--|-----------------------------|-----------------------|-------------------------|---------------------------------|
| Glass Options | Energy Rating | U-value (metric) | U-value (imperial) | Solar Heat Gain Coefficient | Visible Transmittance | Condensation Resistance | Canadian Energy Star Zones 2015 |
| Clear | 16 | 2.4 | 0.43 | 0.51 | 0.53 | 44 | No/non |
| Clear w Grilles | 13 | 2.4 | 0.43 | 0.46 | 0.48 | 44 | No/non |
| LoE/Argon | 29 | 1.7 | 0.30 | 0.46 | 0.52 | 58 | 1 2 |
| LoE/Argon w Grilles | 26 | 1.7 | 0.30 | 0.41 | 0.47 | 58 | 1 |
| Energlass | 30 | 1.6 | 0.29 | 0.46 | 0.52 | 60 | 1 2 |
| Energlass w Grilles | 27 | 1.6 | 0.29 | 0.41 | 0.47 | 60 | 1 |
| LoE/Argon-LSG | 19 | 1.6 | 0.28 | 0.25 | 0.46 | 60 | 1 |
| LoE/Argon-LSG w Grilles | 18 | 1.6 | 0.28 | 0.23 | 0.41 | 60 | 1 |
| Energlass-LSG | 21 | 1.5 | 0.27 | 0.25 | 0.46 | 62 | 1 |
| Energlass-LSG w Grilles | 19 | 1.5 | 0.27 | 0.23 | 0.41 | 62 | 1 |
| Triple Clear | 29 | 1.7 | 0.30 | 0.46 | 0.49 | 61 | 1 2 |
| Triple w Grilles | 27 | 1.7 | 0.30 | 0.42 | 0.44 | 61 | 1 |
| Triple LoE/Argon x 1 LSG | 26 | 1.2 | 0.22 | 0.23 | 0.41 | 72 | 1 2 |
| Triple LoE/Argon x 1 LSG w Grilles | 24 | 1.2 | 0.22 | 0.21 | 0.37 | 72 | 1 2 |
| Energls Plus Argon LSG | 29 | 1.0 | 0.18 | 0.20 | 0.35 | 77 | 1 2 3 |
| Energls Plus Argon LSG w Grilles | 28 | 1.0 | 0.18 | 0.18 | 0.32 | 77 | 1 2 3 |
| Triple LoE/Argon x 1 | 36 | 1.2 | 0.22 | 0.41 | 0.48 | 69 | 1 2 3 |
| Triple LoE/Argon x 1 w Grilles | 34 | 1.2 | 0.22 | 0.37 | 0.43 | 69 | 1 2 3 |
| Energls Plus Argon | 38 | 1.1 | 0.19 | 0.39 | 0.47 | 76 | 1 2 3 |
| Energls Plus Argon w Grilles | 37 | 1.1 | 0.19 | 0.36 | 0.43 | 76 | 1 2 3 |

| Select Casement Fixed Sash | | NAFS Ratings | | NFRC/Energy Star: NFRC | | AAMA/WDMA/CSA/1.S.2-/A440-08: LC-PG40-FW | | Size Tested: (60"x39.75") | |
|------------------------------------|----------------------|-------------------------|---------------------------|------------------------------------|------------------------------|---|--|---------------------------|--|
| Glass Options | Energy Rating | U-value (metric) | U-value (imperial) | Solar Heat Gain Coefficient | Visible Transmittance | Condensation Resistance | Canadian Energy Star Zones 2015 | | |
| Clear | 20 | 2.5 | 0.44 | 0.60 | 0.63 | 44 | No/non | | |
| Clear w Grilles | 16 | 2.5 | 0.44 | 0.54 | 0.56 | 44 | No/non | | |
| LoE/Argon | 36 | 1.6 | 0.28 | 0.54 | 0.62 | 59 | 1 2 3 | | |
| LoE/Argon w Grilles | 33 | 1.6 | 0.28 | 0.48 | 0.55 | 59 | 1 2 | | |
| Energlass | 36 | 1.6 | 0.28 | 0.54 | 0.62 | 61 | 1 2 3 | | |
| Energlass w Grilles | 33 | 1.6 | 0.28 | 0.48 | 0.55 | 61 | 1 2 | | |
| LoE/Argon-LSG | 24 | 1.5 | 0.27 | 0.30 | 0.54 | 60 | 1 | | |
| LoE/Argon-LSG w Grilles | 22 | 1.5 | 0.27 | 0.27 | 0.48 | 60 | 1 | | |
| Energlass-LSG | 24 | 1.5 | 0.26 | 0.30 | 0.54 | 62 | 1 | | |
| Energlass-LSG w Grilles | 22 | 1.5 | 0.26 | 0.27 | 0.48 | 62 | 1 | | |
| Triple Clear | 34 | 1.7 | 0.30 | 0.55 | 0.58 | 61 | 1 2 3 | | |
| Triple w Grilles | 31 | 1.7 | 0.30 | 0.49 | 0.51 | 61 | 1 2 | | |
| Triple LoE/Argon x 1 LSG | 29 | 1.2 | 0.21 | 0.27 | 0.49 | 71 | 1 2 3 | | |
| Triple LoE/Argon x 1 LSG w Grilles | 28 | 1.2 | 0.21 | 0.25 | 0.44 | 71 | 1 2 3 | | |
| Energlass Plus Argon LSG | 33 | 0.9 | 0.16 | 0.23 | 0.42 | 78 | 1 2 3 | | |
| Energlass Plus Argon LSG w Grilles | 32 | 0.9 | 0.16 | 0.21 | 0.37 | 78 | 1 2 3 | | |
| Triple LoE/Argon x 1 | 42 | 1.2 | 0.21 | 0.49 | 0.57 | 70 | 1 2 3 | | |
| Triple LoE/Argon x 1 w Grilles | 39 | 1.2 | 0.21 | 0.44 | 0.51 | 70 | 1 2 3 | | |
| Energlass Plus Argon | 46 | 1.0 | 0.17 | 0.47 | 0.56 | 77 | 1 2 3 | | |
| Energlass Plus Argon w Grilles | 43 | 1.0 | 0.17 | 0.42 | 0.50 | 77 | 1 2 3 | | |

| Select Narrow Picture Window | | NAFS Ratings | | NFRC/Energy Star: NFRC | | AAMA/WDMA/CSA/1.S.2-/A440-08: LC-PG40-FW | | Size Tested: (60"x39.75") | |
|-------------------------------------|----------------------|-------------------------|---------------------------|------------------------------------|------------------------------|---|--|---------------------------|--|
| Glass Option | Energy Rating | U-value (metric) | U-value (imperial) | Solar Heat Gain Coefficient | Visible Transmittance | Condensation Resistance | Canadian Energy Star Zones 2015 | | |
| Clear | 22 | 2.6 | 0.46 | 0.68 | 0.71 | 44 | No/non | | |
| Clear w Grilles | 18 | 2.6 | 0.46 | 0.61 | 0.64 | 44 | No/non | | |
| LoE/Argon | 39 | 1.7 | 0.29 | 0.61 | 0.70 | 54 | 1 2 3 | | |
| LoE/Argon w Grilles | 35 | 1.7 | 0.29 | 0.55 | 0.63 | 54 | 1 2 3 | | |
| Energlass | 40 | 1.6 | 0.28 | 0.61 | 0.70 | 56 | 1 2 3 | | |
| Energlass w Grilles | 37 | 1.6 | 0.28 | 0.55 | 0.63 | 56 | 1 2 3 | | |
| LoE/Argon-LSG | 25 | 1.5 | 0.27 | 0.33 | 0.61 | 59 | 1 | | |
| LoE/Argon-LSG w Grilles | 24 | 1.5 | 0.27 | 0.30 | 0.54 | 59 | 1 | | |
| Energlass-LSG | 26 | 1.5 | 0.26 | 0.33 | 0.61 | 61 | 1 | | |
| Energlass-LSG w Grilles | 25 | 1.5 | 0.26 | 0.30 | 0.54 | 61 | 1 | | |
| Triple | 37 | 1.8 | 0.31 | 0.62 | 0.65 | 61 | 1 2 3 | | |
| Triple w Grilles | 34 | 1.8 | 0.31 | 0.56 | 0.58 | 61 | 1 2 3 | | |
| Triple LoE/Argon x 1 | 46 | 1.2 | 0.21 | 0.55 | 0.64 | 70 | 1 2 3 | | |
| Triple LoE/Argon x 1 w Grilles | 43 | 1.2 | 0.21 | 0.50 | 0.57 | 70 | 1 2 3 | | |
| Triple LoE/Argon x 1 LSG | 32 | 1.2 | 0.21 | 0.31 | 0.55 | 71 | 1 2 3 | | |
| Triple LoE/Argon x 1 LSG w Grilles | 30 | 1.2 | 0.21 | 0.28 | 0.50 | 71 | 1 2 3 | | |
| Energlass Plus Argon | 50 | 0.9 | 0.16 | 0.53 | 0.63 | 76 | 1 2 3 | | |
| Energlass Plus Argon w Grilles | 48 | 0.9 | 0.16 | 0.48 | 0.56 | 76 | 1 2 3 | | |
| Energlass Plus Argon LSG | 36 | 0.9 | 0.15 | 0.26 | 0.47 | 78 | 1 2 3 | | |
| Energlass Plus Argon LSG w Grilles | 35 | 0.9 | 0.15 | 0.24 | 0.42 | 78 | 1 2 3 | | |

| Select Wide Picture Window | NAFS Ratings | Range | | | | | |
|------------------------------------|---------------|------------------------|--|-----------------------------|--|-------------------------|---------------------------------|
| | | NFRC/Energy Star: NFRC | AAMA/WDMA/CSA/I.S.2-/A440-08: CW-PG45-FW Size Tested: (60"x96") | | AAMA/WDMA/CSA/I.S.2-/A440-08: CW-PG60-FW Size Tested: (80"x34") | | |
| Glass Options | Energy Rating | U-value (metric) | U-value (imperial) | Solar Heat Gain Coefficient | Visible Transmittance | Condensation Resistance | Canadian Energy Star Zones 2015 |
| Clear | 20 | 2.5 | 0.44 | 0.61 | 0.63 | 44 | N/A |
| Clear w Grilles | 16 | 2.5 | 0.44 | 0.54 | 0.56 | 44 | N/A |
| LoE/Argon | 36 | 1.6 | 0.28 | 0.54 | 0.62 | 58 | 1 2 3 |
| LoE/Argon w Grilles | 33 | 1.6 | 0.28 | 0.49 | 0.55 | 58 | 1 2 |
| Energlass | 36 | 1.6 | 0.28 | 0.54 | 0.62 | 57 | 1 2 3 |
| Energlass w Grilles | 33 | 1.6 | 0.28 | 0.49 | 0.55 | 57 | 1 2 |
| LoE/Argon-LSG | 24 | 1.5 | 0.27 | 0.30 | 0.54 | 59 | 1 |
| LoE/Argon-LSG w Grilles | 22 | 1.5 | 0.27 | 0.27 | 0.48 | 59 | 1 |
| Energlass-LSG | 25 | 1.5 | 0.26 | 0.30 | 0.54 | 62 | 1 |
| Energlass-LSG w Grilles | 23 | 1.5 | 0.26 | 0.27 | 0.48 | 62 | 1 |
| Triple Clear | 34 | 1.7 | 0.30 | 0.55 | 0.58 | 61 | 1 2 3 |
| Triple w Grilles | 31 | 1.7 | 0.30 | 0.49 | 0.51 | 61 | 1 2 |
| Triple LoE/Argon x 1 LSG | 30 | 1.2 | 0.21 | 0.28 | 0.49 | 71 | 1 2 3 |
| Triple LoE/Argon x 1 LSG w Grilles | 28 | 1.2 | 0.21 | 0.25 | 0.44 | 71 | 1 2 3 |
| Energlass Plus Argon LSG | 35 | 0.9 | 0.15 | 0.24 | 0.42 | 79 | 1 2 3 |
| Energlass Plus Argon LSG w Grilles | 33 | 0.9 | 0.15 | 0.21 | 0.37 | 79 | 1 2 3 |
| Triple LoE/Argon x 1 | 42 | 1.2 | 0.21 | 0.49 | 0.57 | 70 | 1 2 3 |
| Triple LoE/Argon x 1 w Grilles | 39 | 1.2 | 0.21 | 0.44 | 0.51 | 70 | 1 2 3 |
| Energlass Plus Argon | 46 | 1.0 | 0.17 | 0.47 | 0.56 | 77 | 1 2 3 |
| Energlass Plus Argon w Grilles | 43 | 1.0 | 0.17 | 0.42 | 0.50 | 77 | 1 2 3 |

| Select Single Hung | NAFS Ratings | Range | | | | | |
|-------------------------|---------------|------------------------|--|-----------------------------|------------------------|-------------------------|---------------------------------|
| | | NFRC/Energy Star: NFRC | AAMA/WDMA/CSA/I.S.2-/A440-08: R-PG35-H | | Size Tested: (40"x80") | | |
| Glass Options | Energy Rating | U-value (metric) | U-value (imperial) | Solar Heat Gain Coefficient | Visible Transmittance | Condensation Resistance | Canadian Energy Star Zones 2015 |
| Clear | 15 | 2.7 | 0.48 | 0.62 | 0.64 | 42 | No/non |
| Clear w Grilles | 11 | 2.7 | 0.48 | 0.55 | 0.58 | 42 | No/non |
| LoE/Argon | 31 | 1.8 | 0.32 | 0.55 | 0.64 | 54 | 1 2 |
| LoE/Argon w Grilles | 28 | 1.8 | 0.32 | 0.50 | 0.57 | 54 | 1 |
| Energlass | 32 | 1.8 | 0.31 | 0.55 | 0.64 | 57 | 1 2 |
| Energlass w Grilles | 30 | 1.8 | 0.31 | 0.50 | 0.57 | 57 | 1 2 |
| LoE/Argon-LSG | 19 | 1.7 | 0.30 | 0.30 | 0.55 | 55 | No/non |
| LoE/Argon-LSG w Grilles | 17 | 1.7 | 0.30 | 0.27 | 0.49 | 55 | No/non |
| Energlass-LSG | 20 | 1.6 | 0.29 | 0.30 | 0.55 | 58 | No/non |
| Energlass-LSG w Grilles | 19 | 1.6 | 0.29 | 0.27 | 0.49 | 58 | No/non |

| Select Single Glider | NAFS Ratings | AAMA/WDMA/CSA/ISO.2-/A440-08: LC-PG30-HS | | | | | | Size Tested: (72"x60") |
|-------------------------|---------------|--|--------------------|-----------------------------|-----------------------|-------------------------|---------------------------------|------------------------|
| | | NFR/Star: NFR | | NFR/Star: NFR | | | | |
| Glass Options | Energy Rating | U-value (metric) | U-value (imperial) | Solar Heat Gain Coefficient | Visible Transmittance | Condensation Resistance | Canadian Energy Star Zones 2015 | |
| Clear | 15 | 2.7 | 0.48 | 0.62 | 0.64 | 42 | No/non | |
| Clear w Grilles | 11 | 2.7 | 0.48 | 0.55 | 0.57 | 42 | No/non | |
| LoE/Argon | 31 | 1.8 | 0.32 | 0.55 | 0.63 | 54 | 1 2 | |
| LoE/Argon w Grilles | 28 | 1.8 | 0.32 | 0.49 | 0.57 | 54 | 1 | |
| Energlass | 32 | 1.8 | 0.31 | 0.55 | 0.63 | 57 | 1 2 | |
| Energlass w Grilles | 29 | 1.8 | 0.31 | 0.49 | 0.57 | 57 | 1 2 | |
| LoE/Argon-LSG | 19 | 1.7 | 0.30 | 0.30 | 0.55 | 55 | No/non | |
| LoE/Argon-LSG w Grilles | 18 | 1.7 | 0.30 | 0.27 | 0.49 | 55 | No/non | |
| Energlass-LSG | 21 | 1.6 | 0.29 | 0.30 | 0.55 | 58 | No/non | |
| Energlass-LSG w Grilles | 19 | 1.6 | 0.29 | 0.27 | 0.49 | 58 | No/non | |

| Select Single Hung Picture Window | NAFS Ratings | AAMA/WDMA/CSA/ISO.2-/A440-08: R-PG40-FW / AAMA/WDMA/CSA/ISO.2-/A440-08: LC-PG55-FW | | | | | |
|-----------------------------------|---------------|--|--------------------|-----------------------------|-----------------------|-------------------------|---------------------------------|
| | | NFR/Star: NFR | | NFR/Star: NFR | | NFR/Star: NFR | |
| Glass Options | Energy Rating | U-value (metric) | U-value (imperial) | Solar Heat Gain Coefficient | Visible Transmittance | Condensation Resistance | Canadian Energy Star Zones 2015 |
| Clear | 20 | 2.6 | 0.46 | 0.65 | 0.68 | 43 | No/non |
| Clear w Grilles | 16 | 2.6 | 0.46 | 0.58 | 0.61 | 43 | No/non |
| LoE/Argon | 36 | 1.7 | 0.30 | 0.58 | 0.67 | 56 | 1 2 3 |
| LoE/Argon w Grilles | 33 | 1.7 | 0.30 | 0.52 | 0.60 | 56 | 1 2 |
| Energlass | 37 | 1.6 | 0.29 | 0.58 | 0.67 | 59 | 1 2 3 |
| Energlass w Grilles | 34 | 1.6 | 0.29 | 0.52 | 0.60 | 59 | 1 2 3 |
| LoE/Argon-LSG | 23 | 1.6 | 0.28 | 0.32 | 0.58 | 58 | 1 |
| LoE/Argon-LSG w Grilles | 21 | 1.6 | 0.28 | 0.29 | 0.52 | 58 | 1 |
| Energlass-LSG | 24 | 1.5 | 0.27 | 0.32 | 0.58 | 60 | 1 |
| Energlass-LSG w Grilles | 23 | 1.5 | 0.27 | 0.29 | 0.52 | 60 | 1 |

| Select Double Hung | NAFS Ratings | Range | | | | | |
|----------------------------|---------------|---------------------------|--------------------|--|--|-------------------------|---------------------------------|
| | | NFRC/Energy Star: NFRC | | AAMA/WDMA/CSA/1.S.2-/A440-08: R-PG35-H Size Tested: (47.785"x72") | AAMA/WDMA/CSA/1.S.2-/A440-08: R-PG50-H Size Tested: (40"x63") | | |
| Glass Options | Energy Rating | U-value (metric) | U-value (imperial) | Solar Heat Gain Coefficient | Visible Transmittance | Condensation Resistance | Canadian Energy Star Zones 2015 |
| Clear | 16 | 2.67 | 0.47 | 0.62 | 0.64 | 42 | - |
| Clear w Grilles | 12 | 2.67 | 0.47 | 0.55 | 0.57 | 42 | - |
| LoE/Argon | 32 | 1.76 | 0.31 | 0.55 | 0.63 | 54 | 1 2 |
| LoE/Argon w Grilles | 29 | 1.76 | 0.31 | 0.5 | 0.56 | 54 | 1 2 |
| Energlass IU | 33 | 1.70 | 0.3 | 0.55 | 0.63 | 53 | 1 2 |
| Energlass IU w Grilles | 30 | 1.70 | 0.3 | 0.5 | 0.56 | 53 | 1 2 |
| Energlass SS | 33 | 1.70 | 0.3 | 0.55 | 0.63 | 57 | 1 2 |
| Energlass SS w Grilles | 30 | 1.70 | 0.3 | 0.5 | 0.56 | 57 | 1 2 |
| LoE/Argon-LSG | 19 | 1.70 | 0.3 | 0.3 | 0.55 | 55 | - |
| LoE/Argon-LSG w Grilles | 17 | 1.70 | 0.3 | 0.27 | 0.49 | 55 | - |
| Energlass IU-LSG | 20 | 1.65 | 0.29 | 0.3 | 0.55 | 58 | - |
| Energlass IU-LSG w Grilles | 18 | 1.65 | 0.29 | 0.27 | 0.49 | 58 | - |
| Energlass SS-LSG | 20 | 1.65 | 0.29 | 0.3 | 0.55 | 58 | - |
| Energlass SS-LSG w Grilles | 18 | 1.65 | 0.29 | 0.27 | 0.49 | 58 | - |

| Select Double Hung Picture Window | NAFS Ratings | NFRC/Energy Star: NFRC | | | | | |
|-----------------------------------|---------------|--|--------------------|-----------------------------|-----------------------|-------------------------|---------------------------------|
| | | No available NAFS Ratings for this product | | | | | |
| Glass Options | Energy Rating | U-value (metric) | U-value (imperial) | Solar Heat Gain Coefficient | Visible Transmittance | Condensation Resistance | Canadian Energy Star Zones 2015 |
| Clear | 18 | 2.7 | 0.47 | 0.64 | 0.68 | 45 | |
| Clear w Grilles | 15 | 2.7 | 0.47 | 0.58 | 0.61 | 45 | |
| LoE/Argon | 37 | 1.7 | 0.30 | 0.59 | 0.67 | 56 | 1 2 3 |
| LoE/Argon w Grilles | 33 | 1.7 | 0.30 | 0.53 | 0.60 | 56 | 1 2 |
| Energlass | 37 | 1.7 | 0.30 | 0.59 | 0.67 | 57 | 1 2 3 |
| Energlass w Grilles | 33 | 1.7 | 0.30 | 0.53 | 0.60 | 57 | 1 2 |
| LoE/Argon-LSG | 24 | 1.6 | 0.28 | 0.33 | 0.59 | 55 | 1 |
| LoE/Argon-LSG w Grilles | 22 | 1.6 | 0.28 | 0.30 | 0.53 | 55 | 1 |
| Energlass-LSG | 24 | 1.6 | 0.28 | 0.33 | 0.59 | 58 | 1 |
| Energlass-LSG w Grilles | 22 | 1.6 | 0.28 | 0.30 | 0.53 | 58 | 1 |